

## RAVENOL ATF Dexron II E

Art.1211103

SYNTHETIC

ATF

### Description:

**RAVENOL ATF Dexron II E** is high performance synthetic automatic transmission oil ATF for use in torque converter transmission and power shift transmission of vehicles with specification GM Dexron II E, Ford Mercon and Allison C-4.

### Application Directions:

**RAVENOL ATF Dexron II E** is developed for use in automatic transmission and torque converter transmission and power shift transmission with required specification.

**RAVENOL ATF Dexron II E** is recommended if ATF Type Dexron II E is to be used according to manufacturer's specification.

### Quality Classification:

**RAVENOL ATF Dexron II E** is approved, tried and tested for aggregates specifying:

Specifications: GM Dexron II E, Ford Mercon

Approvals: MB-Approval 236.8, Voith 55.6336.3x Extended Drain (G1363), Allison C4-32652009 (ATF II E)

Recommendations: MB 236.5, MAN 339 Type Z-2, MAN 339 Type V-2, ZF TE-ML 04D, 09X, 14B, 16L, Cat. TO-2

### Technical Characteristics:

**RAVENOL ATF Dexron II E** offers:

- reliable protection against wear, sludge, adhesion and corrosion
- a very shear stable viscosity-temperature behaviour
- can be used both at very low and very high temperatures
- an extremely high thermal load
- No foaming, even under the heaviest loads
- compatibility with sealing materials

### Technical Values:

| Characteristics               | Unit               | Data  | Test according to |
|-------------------------------|--------------------|-------|-------------------|
| Density at 20°C               | kg/m <sup>3</sup>  | 834,0 | EN ISO 12185      |
| Colour                        |                    | red   | visual            |
| Viscosity at 100°C            | mm <sup>2</sup> /s | 7,5   | DIN 51562-1       |
| Viscosity at 40°C             | mm <sup>2</sup> /s | 32,0  | DIN 51562-1       |
| Viscosity Index VI            |                    | 191   | DIN ISO 2909      |
| Brookfield Viscosity at -40°C | mPa*s              | 8.300 | ASTM D2983        |
| Pourpoint                     | °C                 | -57   | DIN ISO 3016      |
| Flashpoint                    | °C                 | 226   | DIN ISO 2592      |
| TBN                           | mg KOH/g           | 1,7   | ASTM D2896        |

All indicated data are approximate values and are subject to the commercial fluctuations.

To the best of our knowledge all information reflects the current state of findings and our development. Subject to change. Any reference to DIN standards are solely for product description purposes and do not represent a guarantee. If problems occur please consult a technician.